ATTORNEY DOCKET: SP00-265A SERIAL NO. 10/679,082 FILED: OCTOBER 3, 2003

GROUP ART UNIT: 1755

EXAMINER: ELIZABETH A. BOLDEN

PAGE 2

- 3. (Currently amended) A-The glass article according to claim 2-1, wherein the transmittance value is above 90 percent at the wavelength ranging from 880 nm to 1,690 nm.
- 4. (Currently Amended) A polarizing glass article comprising a base glass <u>selected from</u> either a copper or copper-cadmium family, or a silver halide-containing glass family having and-precipitated silver particles wherein the polarizing glass article exhibits a contrast ratio of at least 50 dB over a wavelength range of 980 nm to 1,640 nm and a bandwidth of 660 nm.
- 5. Cancelled
- 6. (Currently amended) A-The glass article according to claim 5-4, wherein the transmittance value is above 90 percent at the wavelength ranging from 980 nm to 1,640 nm.
- 7. (Currently amended) A-The glass article according to claim 6, wherein the glass article has a center wavelength of at least 1,550 nm or longer.
- 8. (Currently amended) A-The glass article according to claim 1, wherein the base glass has a composition consisting essentially, in weight percent, of about 0-2.5% Li₂O, 0-9% Na₂O, 0-17% K₂O, 0-6% Cs₂O, 8-20% total of Li₂O+-Na₂O+K₂O+Cs₂O, 14-23% B₂O₃, 5-25% Al₂O₃, 0-25% P₂O₅, 20-65% SiO₂, 0.004-0.02% CuO, 0.15-0.3% Ag, 0.1-0.2% Br, and 0.1-0.25% Cl.
- 9. (Currently amended) A-The glass article according to claim 8, wherein said glass includesing as optional constituents, up to about 10% total of other oxides or elements selected in amounts not exceeding the indicated proportions from the group consisting of up to 6% ZrO₂, up to 3% TiO₂, up to 0.5% PbO, up to 7% BaO, up to 4% CaO, up to 3% MgO, up to 6% Nb₂O₅, up to 4% La₂O₃ and up to 2%F.

Please add new claim 21 as follows:

21. The glass article according to claim 8, wherein a molar ratio of alkali metal oxides, B₂O₃ ranges between about 0.55-0.85, and a weight ratio of Ag(Cl+Br) ranges between about 0.65-0.95.